

MARVEL PRO Wall



WHITEBODY WALL TILES
WHITEBODY WALL TILES
Compliant with standards EN 14411:2012 annex L group BIII
Compliant with standards EN 14411:2012 annex L group BIII



Sizes Sizes	50x110 cm 19 5/8"x43 1/4" ± 8.5mm	30.5x91.5 cm 12"x36" ± 8.5mm	40x80 cm 15 3/4" x 31 1/2" ± 10mm	40x80 cm 15 3/4" x 31 1/2" ± 8.5mm	
----------------	---	------------------------------------	---	--	--

TECHNICAL FEATURES / TECHNICAL FEATURES				Requirements for nominal size N			MARVEL PRO WALL	
				7 cm ≤ N < 15 cm	N ≥ 15 cm		Shiny	3D Shiny
				(mm)	(%)	(mm)		
Regularity features		Length and width Length and width	ISO 10545-2	± 0,75 (*)	± 0,5 (*)	± 2,0 (*)	±0.3% ±1.0mm	±0.3% ±1.0mm
		Thickness Thickness		± 0,5 (**)	± 10 (**)	± 0,5 (**)	±10.0% ±0.5mm	±10.0% ±0.5mm
		Straightness of sides Straightness of sides		± 0,5 (***)	± 0,3 (***)	± 1,5 (***)	±0.3% ±0.8mm	±0.3% ±0.8mm
		Rectangularity Rectangularity		± 0,75 (****)	± 0,5 (****)	± 2,0 (****)	±0.3% ±1.5mm	±0.3% ±1.5mm
		Surface flatness Surface flatness		c.c. + 0,75 - 0,50	c.c. + 0,5 - 0,3	c.c. + 2,0 - 1,5	±0.3% ±1.5mm	±0.3% ±1.5mm
				e.c. + 0,75 - 0,50	e.c. + 0,5 - 0,3	e.c. + 2,0 - 1,5		
				w. ± 0,75	w. ± 0,5	w. ± 2,0		
			EN 14411 annex L (Group BIII) EN 14411 annex L (Group BIII)	ISO 13006 annex L (Group BIII) ISO 13006 annex L (Group BIII)				
Structural features		Water absorption level (in% by mass) Water absorption level (in% by mass)	ISO 10545-3	Average >10%. When the average > 20%, this shall be indicated. Individual value > 9% Average >10%. When the average > 20%, this shall be indicated. Individual value > 9%		10%<EB≤20%	10%<EB≤20%	
Bulk mechanical features		Breaking strength Breaking strength	ISO 10545-4	S ≥ 600 N		S ≥600 N	S ≥600 N	
		Modulus of Rupture Modulus of Rupture		R ≥ 15 N/mm2		R ≥15 N/mm ²	R ≥15 N/mm ²	
Thermo-igrometric features		Linear Thermal Expansion Coefficient Linear Thermal Expansion Coefficient	ISO 10545-8	Declare a value Declare a value	Test method available Test method available	≤7 1/mk	≤7 1/mk	
		Thermal shock resistance Thermal shock resistance	ISO 10545-9	Pass according to EN ISO 10545-1 Pass according to EN ISO 10545-1	Test method available Test method available	Resiste	Resiste	
		Expansion due to humidity (mm/m) Expansion due to humidity (mm/m)	ISO 10545-10	Declare a value Declare a value	Test method available Test method available	≤0.06% (0.6mm/m)	≤0.06% (0.6mm/m)	
		Frost resistance Frost resistance	ISO 10545-12	Pass according to EN ISO 10545-1 Pass according to EN ISO 10545-1	Required Required	0	0	
Physical properties		Bond strength/adhesion for improved cementitious adhesives Bond strength/adhesion for improved cementitious adhesives	EN 1348	Declare a value Declare a value	-	≥1.0 N/mm ² (Class C2 - EN 12004)	≥1.0 N/mm ² (Class C2 - EN 12004)	
		Reaction to fire Reaction to fire	-	Class A1 or A1 _{fl} Class A1 or A1 _{fl}	-	A1	A1	
Chemical features		Resistance to household chemicals and swimming pool salts Resistance to household chemicals and swimming pool salts	ISO 10545-13	Minimum Class B (GB for unglazed tiles) Minimum Class B (GB for unglazed tiles)		GA	GA	
		Resistance to low concentrations of acids and alkalis Resistance to low concentrations of acids and alkalis		Declare a class Declare a class	Test method available Test method available	GLA	GLA	
		Resistance to high concentrations of acids and alkalis Resistance to high concentrations of acids and alkalis		Declare a class Declare a class	Test method available Test method available	GHA	GHA	
		Resistance to staining for glazed tiles Resistance to staining for glazed tiles	ISO 10545-14	Minimum Class 3 Minimum Class 3		GA	GA	

(*) The permissible deviation, in % or mm, of the average size for each tile (2 or 4 sides) from work size (W).
(**) The permissible deviation, in % or mm, of the average thickness for each tile from the work size thickness (W).
(***) The maximum permissible deviation from straightness, in % or mm, related to the corresponding work sizes (W).
(****) The maximum permissible deviation from rectangularity, in % or mm, related to the corresponding work sizes (W).
c.c. The maximum permissible deviation from centre curvature, in % or mm, related to diagonal calculated from the work sizes (W).
e.c. The maximum permissible deviation from edge curvature, in % or mm, related to the corresponding work sizes (W).
w The maximum permissible deviation from warpage, in % or mm, related to diagonal calculated from the work sizes (W).
(1) Requirements european standard EN 176.
(2) Determination of slip resistance of pedestrian surfaces; it does not cover sports surfaces and road surfaces for vehicles (skid resistance).
Anti-slip performance is guaranteed at the time of delivery of the product

